



Estetic[®] Access

Properties	Thermosetting paint	
Applications	Liners, furniture, indoor building applications	
Description	Thickness	15 microns
	Composition	Front: 15 microns top coat Back: 5 or 7 microns backing coat
	Gloss	20-30 GU
	Colour	A9002, A9010, A9881 Other colours on request
	Appearance	Smooth
	Temporary protection (optional)	Self-adhesive film or heat-sealed film
	Performance	Adhesion of the coating
Resistance to cracking on bending		≤ 3 T
Impact resistance		15 J
Clemen scratch resistance		≥ 1 kg
Surface "pencil" hardness		HB to H
Salt spray test		150 hours
Remarks	These performance characteristics refer specifically to metal coating Z100. If any product (film, oil, foam, glue, paint etc) is applied after coil delivery, compatibility with the coating has to be checked.	