

Estetic[®] Tex

Properties	Thermosetting paint	<ul style="list-style-type: none"> • Very good resistance to abrasion • Good formability • Very good surface hardness
Applications	Metal furniture, shelves and shelving units, housings of domestic appliances, air conditioners, radiators, casings etc	
Description	Thickness	35 microns
	Composition	Front: 20 microns of coloured base coat + 15 microns of textured varnish Back: 5, 7, 10 or 12 microns backing coat
	Gloss (Gardner 60°)	Usual: 30-50 GU
	Colours	Specific colours on request
	Appearance	Textured
	Temporary protection (optional)	Not applicable
	Performance	Adhesion of the coating
Resistance to cracking on bending		≤ 2 T
Impact resistance		18 J
Surface "pencil" hardness		H to 2H
Salt spray test		240 hours
Resistance to acids and bases		Good to very good
Resistance to solvents: <ul style="list-style-type: none"> • Aliphatics and alcohols • Ketones • Aromatics 		Very good Low Good
Resistance to mineral oils		Very good
Remarks	These performance characteristics refer specifically to metal coating Z100. If any product (film, oil, foam, glue, paint etc) is applied after coil delivery, compatibility with the coating has to be checked.	